

耐薬品性一覧

用途	製品名																										
	デブコンA	デブコンB	デブコンSF	デブコンST	デブコンF	デブコンF-2	デブコンWR・WR-2	チタニウムパテ	ブラッシュアップセラミック	セラミックリペアー	デブコンUW	マジックボンド	ファインロード	コンボウエアーフC	ウェアガードハイテンプ	フレクサン80L・80P	フレクサン94L	EC7000AR	PWI	PWII	デیفエンスブロック	デブコンPM	RiFlex	フロアパッチFC	JP-2500	シライトRTV	
酸	酢酸(希釈)10%	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	○	○	-	-	-	-	-	-	
	氷酢酸	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	-	-	-	-	-	-	-	-	
	塩酸10%	○	○	△	○	○	○	◎	◎	◎	△	△	○	○	◎	○	○	◎	△	○	○	◎	○	○	○	×	
	塩酸36%	×	×	×	×	×	×	△	△	△	×	×	△	△	◎	○	○	◎	-	-	-	△	○	-	○	×	
	硫酸10%	○	○	△	○	○	○	○	○	○	△	△	○	○	◎	○	○	◎	◎	○	○	◎	-	○	○	○	
	硫酸50%	×	×	×	×	×	×	△	△	△	×	×	×	×	△	○	○	◎	-	-	-	◎	-	-	×	-	
	硫酸98%	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	◎	-	-	-	-	-	-	-	-	
	硝酸10%	△	△	△	△	△	△	○	○	○	△	△	△	△	△	○	△	△	◎	-	-	-	○	-	-	○	-
	硝酸50%	×	×	×	×	×	×	△	△	△	×	×	×	△	△	△	△	△	-	-	-	△	-	-	-	△	
	リン酸10%	△	△	△	△	△	△	○	○	○	△	△	△	△	△	○	○	◎	-	-	△	○	△	-	-	-	-
	リン酸50%	×	×	×	×	×	×	△	△	△	×	×	×	△	△	△	△	◎	-	-	-	△	-	-	-	-	
アルコール	メタノール	×	×	×	×	△	×	×	◎	◎	◎	×	×	×	×	△	×	×	×	△	△	×	◎	-	△	-	△
	イソプロパノール	×	×	×	×	×	×	◎	◎	◎	×	×	×	△	△	×	×	×	◎	◎	-	◎	×	-	-	◎	
ケトン	アセトン	×	×	×	×	×	×	×	×	×	×	×	×	×	△	×	×	×	×	×	-	-	-	-	-	-	
	メチルエチルケトン	×	×	×	×	×	×	×	×	×	×	×	×	○	△	×	×	×	×	×	×	×	×	-	-	×	
アルカリ	水酸化アンモニウム20%	○	○	△	○	×	△	○	◎	◎	◎	○	○	◎	◎	◎	○	○	○	△	-	◎	-	-	○	○	
	水酸化カリウム20%	○	○	△	○	×	△	○	◎	◎	◎	○	△	◎	◎	◎	○	○	-	-	-	◎	○	-	○	◎	
	水酸化カリウム40%	○	○	×	○	×	△	○	◎	◎	◎	○	×	◎	◎	◎	○	○	-	-	-	◎	○	-	○	-	
	水酸化ナトリウム10%	○	○	△	○	△	△	○	◎	◎	◎	○	○	◎	◎	◎	○	○	◎	◎	◎	◎	◎	○	○	◎	◎
	水酸化ナトリウム20%	○	○	×	○	×	△	○	◎	◎	◎	○	×	◎	◎	◎	○	○	◎	-	-	◎	◎	○	○	◎	◎
炭化水素	ベンゼン	△	△	△	○	△	△	○	◎	◎	◎	○	△	○	◎	◎	×	×	◎	-	-	-	-	-	-	-	
	ガンリン(無鉛)	○	○	○	○	○	○	◎	◎	◎	○	○	◎	△	◎	×	×	◎	◎	◎	△	◎	△	-	○	×	
	ミネラルスピリッツ	○	○	○	○	○	○	◎	◎	◎	○	○	◎	◎	◎	×	×	◎	◎	◎	-	◎	-	◎	○	-	
	灯油	○	○	○	○	○	○	◎	◎	◎	○	○	◎	◎	◎	×	×	◎	-	-	-	◎	-	◎	-	-	
	トルエン	△	△	△	○	△	△	△	◎	◎	◎	○	△	◎	◎	◎	×	×	◎	-	-	◎	◎	-	×	-	
	キシレン	△	△	△	○	△	△	△	◎	◎	◎	○	△	◎	◎	◎	×	×	◎	-	-	-	-	×	-	○	-
塩素化炭化水素	四塩化炭素	○	○	×	○	○	△	○	○	○	×	○	○	◎	×	×	×	-	-	-	-	-	-	-	-	-	
	塩化メチレン	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	×	-	-	-	-	-	-	-	×	
	パークロロエチレン	○	○	△	○	○	△	◎	◎	◎	○	△	○	○	◎	×	×	×	△	△	-	-	-	-	○	-	
	1,1,1-トリクロロエタン	○	○	△	○	○	◎	◎	◎	◎	○	△	○	○	◎	×	×	×	-	-	○	-	×	-	-	-	
塩	硫酸アルミニウム10%	○	○	△	○	○	○	◎	◎	◎	○	△	○	○	◎	○	○	◎	-	-	-	-	-	-	-	-	
	炭酸ナトリウム10%	○	○	△	○	○	○	◎	◎	◎	○	△	○	○	◎	○	○	◎	-	-	-	-	-	-	-	-	
	リン酸ナトリウム10%	○	○	△	○	○	○	◎	◎	◎	○	△	○	○	◎	○	○	◎	○	○	○	-	-	-	○	-	
	食塩水	○	○	△	○	○	○	◎	◎	◎	○	△	○	○	◎	○	○	◎	○	○	-	◎	-	-	○	-	
その他	カッティングオイル*	○	○	○	○	○	○	◎	◎	◎	○	○	○	○	◎	×	×	◎	-	-	-	◎	△	-	○	○	
	ビール	○	○	×	○	○	△	◎	◎	◎	○	×	○	○	◎	△	△	◎	-	-	-	-	-	-	-	-	
	ワイン	○	○	×	○	○	△	◎	◎	◎	△	×	△	○	◎	△	△	◎	-	-	-	-	-	-	-	-	
	コーンオイル	○	○	○	○	○	○	◎	◎	◎	○	○	○	○	◎	△	△	◎	-	-	-	-	-	-	-	-	
	次亜塩素酸ナトリウム	○	○	△	○	○	○	◎	◎	◎	○	△	○	○	◎	△	△	◎	-	-	-	◎	○	-	-	○	
	砂糖水	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	◎	-	-	-	-	-	-	-	-	

*種類によりもたないものがありますので、ご注意ください。

◎…優 ○…良 △…可 ×…不可 -…データ無し